

BAYFAST® Yellow Y5688

Chemical description	Azo complex	
Form supplied	yellow powder	
Shade	yellow with a green cast	
Density (23°C)	approx. 1.8g/cm ³	(according to DIN ISO 787-10)
Bulk density	approx. 0.6g/cm ³	(according to DIN ISO 787-11)
Main fields of application	colorant in automotive and high-quality industrial coatings	
Storage stability	60 months from delivery ex plant LANXESS Deutschland GmbH	
Specific surface BET	approx. 110 m ² /g	(DIN ISO 9277)
Particle size x₅₀	0.10 – 0.13 µm	
pH-Value	5 – 7	(DIN ISO 787-9)
Oil absorption	approx. 65g / 100g	(DIN ISO 787-5)
Fastness to acid	5	
Fastness to alkali	5	
Lightfastness	1/3 ST	8
Weatherfastness	1/3 ST	5
Heat stability	200°C	
Fastness to overspraying	5	

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Edition: April 2011
Replace edition: May 2009

LANXESS Deutschland GmbH
Functional Chemicals
Colorants for Plastics
D-51369 Leverkusen

www.lanxess.com

COLORANTS

