

® = registered Trademark of BASF SE

Tinuvin® 622

Oligomeric hindered amine light stabilizer (HALS)

Characterization

Tinuvin 622 is the light stabilizer of choice for all applications calling for low volatility and minimal migration, because of its oligomeric structure with high molecular weight. Furthermore Tinuvin 622 is effective as antioxidant and contributes significantly to the long-term heat stability of polyolefins and tackifier resins.

Chemical name

Butanedioic acid, dimethylester, polymer with 4-hydroxy-2,2,6,6-tetramethyl-1-piperidine ethanol


CAS number

65447-77-0

Structure

Tinuvin 622

Chemical formula



Molecular weight

$M_n = 3100 - 4000$

Applications

Tinuvin 622 areas of application include polyolefins (PP, PE), olefin copolymers such as EVA as well as blends of polypropylene with elastomers. In addition Tinuvin 622 is highly effective in polyacetals, polyamides and polyurethane applications.

Features/benefits

The effectiveness of Tinuvin 622 surpasses significantly that of UV absorbers, particularly in pigmented systems. Combinations of Tinuvin 622 with UV absorbers, e. g. Tinuvin range or other HALS, e. g. Chimassorb® range in many cases result in synergistic effects. Typical examples are Tinuvin 783 and Tinuvin 111.

Product forms

Code: Tinuvin 622 SF
Appearance: Colorless to light yellowish micro granules

Guidelines for use

Thick sections*	UV stabilization of HDPE, LLDPE, LDPE and PP	0.15–0.5 %
Films	UV stabilization of LDPE and LLDPE	0.1–1.2 %
Tapes	UV stabilization of HDPE and PP	0.2–0.8 %
Fibers	UV stabilization of PP fibers	0.1–1.0 %

* The presence of an UV absorber (e. g. TINUVIN 326/328 and Chimassorb 81) is recommended in unpigmented or slightly pigmented articles or to improve the light fastness of certain organic pigments.

Physical Properties

Melting Range	50–70 °C
Flashpoint	> 250 °C
Specific Gravity (20 °C)	1.22 g/cm ³
Vapor Pressure (20 °C)	2.5 E-6 Pa
Bulk density	500–700 g/l

Solubility (20 °C)	% w/w
Acetone	4.0
Chloroforme	> 40
Ethanol	0.08
Ethyl acetate	3.0
n-Hexane	< 0.01
Methanol	0.05
Methylene chloride	> 40
Toluene	15
Water	1.6 mg/l

Volatility	Pure substance; TGA, heating rate 20 °C/ min in air
Weight Loss (%)	Temperature °C
0.1	200
0.2	225
0.4	250
1.1	275
3.1	300
8.4	325

Note

The descriptions, designs, data and information contained herein are presented in good faith, and are based on BASF's current knowledge and experience. They are provided for guidance only, and do not constitute the agreed contractual quality of the product or a part of BASF's terms and conditions of sale. Because many factors may affect processing or application/use of the product, BASF recommends that the reader carry out its own investigations and tests to determine the suitability of a product for its particular purpose prior to use. It is the responsibility of the recipient of product to ensure that any proprietary rights and existing laws and legislation are observed. No warranties of any kind, either expressed or implied, including, but not limited to, warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth herein, or that the products, descriptions, designs, data or information may be used without infringing the intellectual property rights of others. Any descriptions, designs, data and information given in this publication may change without prior information. The descriptions, designs, data and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained, all such being given and accepted at the reader's risk.

March 2011